

Product: WORKRITE[®] MASONRY CEMENT

Type: Type N

Color: Colored

TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTY	WORKRITE [®]	ASTM C 91
Compressive Strength		
7 Day Minimum	1320 psi	500 psi
28 Day Minimum	1370 psi	900 psi
Air Content	16.2%	8% Min. 21% Max.
Water Retention	81.9%	70% Min.

Tests were independently performed according to ASTM Standard C 91 utilizing sand conforming to ASTM Standard C 778.