

Product: WORKRITE® MORTAR CEMENT

Type: Type N

Color: Colored

Pre-Blended  
With



## TYPICAL PHYSICAL PROPERTIES

| PHYSICAL PROPERTY    | WORKRITE® | ASTM C 270 |
|----------------------|-----------|------------|
| Compressive Strength |           |            |
| 7 Day Minimum        | 3265 psi  |            |
| 28 Day Minimum       | 3759 psi  | 750 psi    |
| Air Content          | 9.5%      | 14% Max.   |
| Water Retention      | 83.9%     | 75% Min.   |

Tests were independently performed according to ASTM Standard C 270 utilizing sand conforming to ASTM Standard C 144.