

Product: WORKRITE® MORTAR CEMENT

Type: Type N

Color: Gray

Pre-Blended
With



TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTY	WORKRITE®	ASTM C 270
Compressive Strength		
7 Day Minimum	3265 psi	
28 Day Minimum	3759 psi	750 psi
Air Content	9.5%	14% Max.
Water Retention	83.9%	75% Min.

Tests were independently performed according to ASTM Standard C 270 utilizing sand conforming to ASTM Standard C 144.