

Product: WORKRITE® MORTAR CEMENT

Type: Type S

Color: Gray

Pre-Blended  
With



## TYPICAL PHYSICAL PROPERTIES

PHYSICAL PROPERTY	WORKRITE®	ASTM C 270
Compressive Strength		
7 Day Minimum	4015 psi	
28 Day Minimum	4579 psi	1800 psi
Air Content	8.9%	12% Max.
Water Retention	77.8%	75% Min.

Tests were independently performed according to ASTM Standard C 270 utilizing sand conforming to ASTM Standard C 144.