

Product: **WORKRITE® MORTAR CEMENT**
Type: **Type N**
Color: **Colored**

Pre-Blended
With



Typical Physical Properties

PHYSICAL PROPERTY	WORKRITE®	ASTM C 270
Compressive Strength		
7 Day Minimum	3265 psi	
28 Day Minimum	3759 psi	750 psi
Air Content	9.5%	14% Max.
Water Retention	83.9%	75% Min.

Tests were independently performed according to ASTM Standard C 270 utilizing sand conforming to ASTM Standard C 144.