

Product: **WORKRITE® PORTLAND CEMENT & LIME**
Type: **Type S**
Color: **Colored**

Typical Physical Properties

PHYSICAL PROPERTY	WORKRITE®	ASTM C 270
Compressive Strength 28 Day	2400 psi	1800 psi Min.
Air Content	6%	12% Max.
Water Retention	78%	75% Min.

Tests were independently performed according to ASTM Standard C 270 utilizing sand conforming to ASTM Standard C 144.